

TEST REPORT

**Product information:**

Client:	Safra Sublime
Product:	Palmapine A+/C+
Nominal thickness:	15mm – 7ply
Production lot:	104533
Production date:	October 2021
Composition:	100% pine
Bonding quality:	Class 3 (Exterior)
Formaldehyde emission	E1 (phenolic resin)
Coating:	-

**Results:**

TEST		RESULTS	TECHNICAL SPECIFICATION
Density (kg/m <sup>3</sup> )		650,41	EN 323
Moisture content (%)		6,58	EN 322
Bending strength (N/mm <sup>2</sup> )		60,62	EN 310
	⊥	27,93	
Bending stiffness – MOE (N/mm <sup>2</sup> )		6953	
	⊥	3104	
Shear strength (N/mm <sup>2</sup> )	Cold water	1,439	EN 314-1
	Boil water	1,263	