

Ferik 20,5x61,5

PAVIMENTO GRES / GRES FLOOR TILE



Gris



Natural

FORMATO / SIZE

20,5x61,5 / 8'' x 24 1/4''

ACABADO/FINISH

Mate / Matt

GRUPO / GROUP

Blla

TIPO/ TYPE

Madera / Wood



PAV. GRES
GRES FLOOR



PASTA ROJA
RED BODY



MATE
MATT



RELIEVE
RELIEF



VARIACIÓN
VARIATION



MADERA
WOOD

DESCRIPCIÓN DEL TEST / TEST DESCRIPTION	VALOR DEL TEST / TEST VALUE	 KTL CERAMICA	NORMA / STANDARD	
Absorción de agua / Water absorption	3%<Ev≤ 6%	Cumple / Complies	UNE-EN ISO 10545-3	
Fuerza de rotura / Breaking Strength	≥1000 N	Cumple / Complies	UNE-EN ISO 10545-4	
Resistencia a la flexión / Modulus of rupture	≥ 22 N/mm2	Cumple / Complies	UNE-EN ISO 10545-4	
Abrasion superficial / Surface Abrasion	-	Valor declarado / Declared value	UNE-EN-ISO 10545-7	
Resistencia al cuarteo / Cracking resistance	Requerido / Requested	Cumple / Complies	UNE-EN ISO 10545-11	
Resistencia a la helada / Frost resistance	Requerido / Requested	Cumple / Complies	UNE-EN ISO 10545-12	
Resistencia al deslizamiento / Slip resistance	Ensayo del péndulo/ Pendulum test	Clase 1 / Class 1	UNE-EN 16165 Anexo C AN 2.6	
	Resistencia al deslizamiento (Péndulo): Método operativo (PTV) /Slip resistance (Pendulum): Pendulum test value(PTV)	-	UNE-EN16165 Anexo C UK SRG	
	Coefficiente de fricción dinámico (D.C.O.F)/ Dynamic coefficient of friction (D.C.O.F)	-	ANSI A137.1-2021	
	Método de la rampa con Pie calzado/ Shod Ramp Test	R9	UNE-EN 16165 Anexo B AN 3.3	
	Método de la rampa con Pie descalzo/ Barefoot Ramp Test	-	UNE-EN 16165 Anexo A AN 3.2	
Resistencia química / Chemical resistance	Productos domésticos y de piscina / Household chemicals and swimming pool salts	Mínimo clase B / Minimum class B	Cumple / Complies	UNE-EN ISO 10545-13
	Ácidos a baja concentración / Low concentration of acids	Mínimo clase LB / Minimum class LB	Valor declarado / Declared value	UNE-EN ISO 10545-13
	Bases a baja concentración / Low concentration of alkalis	Mínimo clase LB / Minimum class LB	Valor declarado / Declared value	UNE-EN ISO 10545-13
Resistencia a las manchas / Stain resistance	Mínimo clase 3 / Minimum Class 3	Cumple / Complies	UNE-EN ISO 10545-14	

17/04/2024

Partida Casablanca 6, 12593 Moncofar, Castellón . Spain

Phone : +34 964 584 069 - email: info@ktlceramica.com - web : www.ktlceramica.es


KTL
 C E R A M I C A