













**TECHNICAL FEATURES
CARATTERISTICHE TECNICHE
TECHNISCHE DATEN
CARACTERISTIQUES TECHNIQUES**

Product, Prodotto, Produkt, Produit: L'ALTRA PIETRA® MUSEO





Rev: 06/02/2018

FEATURE CARATTERISTICA DATEN CARACTÉRISTIQUE		TECHNICAL FEATURES CARATTERISTICHE TECNICHE TECHNISCHE DATEN CARACTÉRISTIQUES TECHNIQUES	STANDARD NORMA NORM NORME	ESTABLISHED LIMITS LIMITI PREVISTI VORGESEHENE GRENZWERTE LIMITES ÉTABLIES		L'ALTRA PIETRA®
REGULARITY REGOLARITÀ REGELMÄßIGKEIT RÉGULARITÉ		LENGHT AND WIDTH LUNGHEZZA E LARGHEZZA LÄNGE UND BREITE LONGUEUR ET LARGEUR	ISO 10545-2	± 0.6 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		THICKNESS SPESSORE DICKE ÉPAISSEUR	ISO 10545-2	± 5.0 %	± 0.5 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		RECTANGULARITY ORTOGONALITÀ RECHTWINKLIGKEIT PERPENDICULARITÉ	ISO 10545-2	± 0.5 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		STRAIGHTNESS OF SIDES RETTILINEITÀ DEGLI SPIGOLI GERADLINIGKEIT DER KANTEN RECTITUDE DES ARETES	ISO 10545-2	± 0.5 %	± 1.5 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		SURFACE FLATNESS PLANARITÀ EBENFLÄCHIGKEIT PLANEITÉ DE SURFACE	ISO 10545-2	± 0.5 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
STRUCTURAL STRUTTURALE STRUKTURELL STRUCTURAL		WATER ABSORPTION ASSORBIMENTO D'ACQUA WASSERAUFNAHME ABSORPTION D'EAU	ISO 10545-3	≤ 0.5 %		COMPLYING CONFORME ERFÜLLT CONFORME
		BREAKING STRENGHT SFORZO DI ROTTURA BRUCHKRAFT FORCE DE RUPTURE	ISO 10545-4	≥ 1300 N		≥ 12000 N
		MODULUS OF RUPTURE MODULO DI ROTTURA BRUHLAST MODULE DE RUPTURE	ISO 10545-4	≥ 35 N/mm ²		≥ 48 N/mm ²
SURFACE SUPERFICIE OBERFLÄCHE SURFACE		ABRASION RESISTANCE RESISTENZA ALL'ABRASIONE ABRIEBFESTIGKEIT RESISTANCE A L'ABRASION	ISO 10545-6	≤ 175 mm ³		COMPLYING CONFORME ERFÜLLT CONFORME
THERMAL HYGROMETRIC TERMO IGROMETRICHE THERMAL HYGROMETRISCH THERMIQUE HYGROMÉTRIQUE		LINEAR THERMAL-EXPANSION DILATAZIONE TERMICA LINEARE LINEARER WÄRMEUSDEHNUNG DILATATION THERMIQUE LINEAIRE	ISO 10545-8	VALUE DECLARED VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE		α ≤ 7 · 10 ⁻⁶ °C
		THERMAL SHOCK RESISTANCE RESISTENZA AGLI SBALZI TERMICI WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN RÉSISTANCE AUX ÉCARTS DE TEMPÉRATURE	ISO 10545-9	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		GUARANTEED GARANTITO GARANTIERT GARANTI
		FROST RESISTANCE RESISTENZA AL GELO FROSTBESTÄNDIGKEIT RÉSISTANCE AU GEL	ISO 10545-12	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		GUARANTEED GARANTITO GARANTIERT GARANTI
		REACTION TO FIRE REAZIONE AL FUOCO REAKTION ZUM FEUER RÉACTION AU FEU	EN 9239-1	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		A1fl

TECHNICAL FEATURES
CARATTERISTICHE TECNICHE
TECHNISCHE DATEN
CARACTERISTIQUES TECHNIQUES

Product, Prodotto, Produkt, Produit: L'ALTRA PIETRA[®] MUSEO

Rev: 06/02/2018

<p>LIGHT LUCE LICHT LUMIÈRE</p>		<p>COLOUR RESISTANCE TO LIGHT EXPOSURE RESISTENZA DEI COLORI ALLA LUCE LICHTECHTHEIT DER FARBEN RÉSISTANCE DES COULEURS À LA LUMIÈRE</p>	<p>DIN 51094</p>	<p>NO NOTICEABLE COLOUR MODIFICATIONS. ASSENZA DI APPREZZABILI ALTERAZIONI DI COLORE. KEIN SICHTBARE FARBVERÄNDERUNGEN AUFWEISEN. AUCUN ALTÉRATIONS APPRÉCIABLES DE COULEUR.</p>	<p>COMPLYING CONFORME ERFÜLLT CONFORME</p>
<p>CHEMICAL CHIMICA CHEMISCH CHIMIQUE</p>		<p>RESISTANCE TO CHEMICALS (ACIDS, BASES AND SALTS) RESISTENZA ALL'ATTACCO CHIMICO (ACIDI, BASI E SALI) CHEMIKALIENBESTÄNDIGKEIT (SÄUREN, BASIS UND SALZ) RESISTANCE A L'ATTAQUE CHIMIQUE (ACIDES, BASES ET SELS)</p>	<p>ISO 10545-13</p>	<p>UB MINIMUM UB MINIMO UB MINIMUM UB MINIMUM</p>	<p>UA ULA UHA GUARANTEED GARANTITO GARANTIERT GARANTI</p>
		<p>RESISTANCE TO STAINS RESISTENZA ALLE MACCHIE FLECKENBESTÄNDIGKEIT RESISTANCE AUX TACHES</p>	<p>ISO 10545-14</p>	<p>≥ 3</p>	<p>5 GUARANTEED 5 GARANTITO 5 GARANTIERT 5 GARANTI</p>
<p>SAFETY SICUREZZA SICHERHEIT SÉCURITÉ</p>		<p>SKID RESISTANCE RESISTENZA ALLO SCIVOLAMENTO RUTSCHHEMMUNG RÉSISTANCE AU GLISSEMENT</p>	<p>DIN 51130</p>	<p>VALUE DECLARED VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE</p>	<p>R11</p>
	<p>DIN 51097</p>	<p>A+B+C</p>			

Compliant with standards EN 14411 (ISO 13006) annex G group Bla
Conforme alla norma EN 14411 (ISO 13006) Appendice G gruppo Bla