


| | | | | |
|--|---|--|---------------------------------------|-------------------------|
| MODELO / MODEL | | Nanotech SERIE STONEAGE 20MM RECT. (MC) (SAND, CONCRETE, ASTH) | | |
| FOTO / PICTURE (orientativa) | |  | | |
| FORMATO / SIZE | | 60 x 60 cms. 20MM Aprox. Rect. | | |
| GRUPO / GROUP | | Bla | | |
| TIPO / TYPE | | PORCELANICO ESMALTADO / Glazed Porcelain Tile | | |
| <u>DESCRIPCION DEL TEST / TEST DESCRIPTION</u> | | <u>VALOR DEL TEST / TEST VALUE</u> | KERATILE | <u>NORMA / STANDARD</u> |
| ABSORCIÓN DE AGUA / WATER ABSORPTION | | AA < 0,5% | Cumple / Passed | UNE-EN-ISO 10545-3 |
| FUERZA DE ROTURA / BREAKING STRENGTH | | > 1300 N | Cumple / Passed | UNE-EN-ISO 10545-4 |
| RESISTENCIA A LA FLEXIÓN / RESISTANCE OF FLEXION | | > 35 N/mm2 | Cumple / Passed | UNE-EN-ISO 10545-4 |
| ABRASION SUPERFICIAL / SURFACE ABRASION | | Clase / Class | SAND, CONCRETE PEI IV ARTH PEI III | UNE-EN-ISO 10545-7 |
| RESISTENCIA AL CUARTEO / CRACKING RESISTANCE | | Requerido / Requested | Cumple / Passed | UNE-EN-ISO 10545-11 |
| RESISTENCIA A LA HELADA / FROST RESISTANCE | | Requerido / Requested | Cumple / Passed | UNE-EN-ISO 10545-12 |
| RESISTENCIA QUIMICA / CHEMICAL RESISTANCE | (PRODUCTOS DOMESTICOS Y DE PISCINA / Domestic & Swimming Pool Products) | Mínimo / Minimum GB | Cumple / Passed | UNE-EN-ISO 10545-13 |
| RESISTENCIA A LOS ACIDOS / ACID RESISTANCE | | GHA | Cumple / Passed | UNE-EN-ISO 10545-13 |
| RESISTENCIA A LAS BASES / ALKALINE RESISTANCE | | GHA | Cumple / Passed | UNE-EN-ISO 10545-13 |
| RESISTENCIA A LAS MANCHAS / RESISTANCE TO STAINS | | Mínimo / Minimum Class 3 | Cumple / Passed | UNE-EN-ISO 10545-14 |
| RESISTENCIA AL DESLIZAMIENTO / SLIP RESISTANCE | | Metodo Disponible / Available Method | Class 3 | UNE-ENV 12633:2003 |
| RESISTENCIA AL RAYADO / HARDNESS (MOHS) | | Mínimo / Minimum 3 | Cumple / Passed | EN 101 |